


**Brick Testing  
(CSA A82.2)**

**Project Name:** P.O. 722275 **Project No.:** BRM-00056208-Z0  
**Manufacture:** Newtonbrook Block  
**Date of Manufacture:** October, 2010 **Date Tested:** December 21, 2010

COMPRESSIVE STRENGTH (MPa)		ABSORPTION	DENSITY (SSD)
Sample No.	Compressive Strength (MPa)	%	(kg/m <sup>3</sup> )
1	43.0	5.6	2280
2	43.8	5.8	2273
3	43.2	6.0	2266
4	42.0	5.7	2272
5	43.1	4.7	2265
<b>Average:</b>	<b>43.0</b>	<b>5.6</b>	<b>2271</b>



Testing Laboratory Representative Signature  
 Ammanuel Yousif, C.E.T.

December 22, 2010  
 Date